

**Cabot's Danish Oil**

**NZDW0830**

<b>Part A</b>	871-82113
---------------	-----------





<b>Description</b>
CABOT'S Danish Oil is a penetrating oil for interior panelling to produce a soft lustre without obvious film build.

<b>Features</b>
<ul style="list-style-type: none"> <li>• Low sheen</li> <li>• Polyurethane resin</li> <li>• Clear finish</li> <li>• Free flowing</li> </ul>

<b>Benefits</b>
<ul style="list-style-type: none"> <li>• Gives "hand-rubbed" appearance</li> <li>• Develops moderate hardness</li> <li>• Enhances grain and colour</li> <li>• Apply with brush or cloth</li> </ul>

<b>Uses</b>
Use CABOT'S Danish Oil on interior timber panelling, trim, furniture and cupboards.

<b>Performance Guide</b>			
<b>Weather</b>	For interior use only, not recommended for exterior use.	<b>Salt</b>	Unaffected by splash or spillage
<b>Heat Resistance</b>	Up to 120C. Premature yellowing and embrittlement will occur if subjected to continuous heat.	<b>Water</b>	Good water resistance.
<b>Solvent</b>	Resists mineral turpentine and similar solvents.	<b>Abrasion</b>	Moderate resistance to abrasion.
<b>Alkali</b>	N/A		

<b>Typical Properties</b>																												
<b>Thinner</b>	Not required		<b>Colour</b>	Clear																								
<b>Components</b>	1		<b>Number Of Coats</b>	2																								
<b>Toxicity</b>	Lead free. Dry film is non-toxic.		<b>V.O.C. Level</b>	590 g/L																								
<b>Sanding Properties</b>	Very good		<b>Touch Dry</b>	3 Hours																								
<b>Clean Up</b>	 Thinner																											
<b>Clean Up Description</b>	Thoroughly clean all equipment with mineral turpentine																											
<b>Application Method</b>	 Brush  Roller  Pad																											
<b>Application Conditions</b>	<table border="0" style="width:100%"> <tr> <td style="text-align:center"><b>Solids By Volume</b></td> <td style="text-align:center">28</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align:center"><b>Min</b></td> <td style="text-align:center"><b>Max</b></td> <td style="text-align:center"><b>Recommended</b></td> </tr> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align:center">100</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align:center">28</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td style="text-align:center">8 Hours</td> <td style="text-align:center">Indefinite</td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td></td> <td></td> <td style="text-align:center">10</td> </tr> </table>				<b>Solids By Volume</b>	28				<b>Min</b>	<b>Max</b>	<b>Recommended</b>	<b>Wet Film Per Coat (microns)</b>			100	<b>Dry Film Per Coat (microns)</b>			28	<b>Recoat Time (min)</b>	8 Hours	Indefinite		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>			10
<b>Solids By Volume</b>	28																											
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>																									
<b>Wet Film Per Coat (microns)</b>			100																									
<b>Dry Film Per Coat (microns)</b>			28																									
<b>Recoat Time (min)</b>	8 Hours	Indefinite																										
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>			10																									

### Application Guide

<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>All timber surfaces should be thoroughly clean, dry and free from wax, oil, grease and other contaminants. Wash with mineral turpentine if needed to remove wax and grease, allow to dry, and lightly sand dressed surfaces with "00" paper or finer, always in direction of the grain.</li> <li>For interior surfaces, fill nail holes with CABOT'S Wood Tone Putty - do not use a linseed oil putty.</li> </ul>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>Brush, short-nap roller or pad</li> <li>Stir contents thoroughly before and during use with a broad flat stirrer, to maintain a uniform colour and solution.</li> </ul> <p>Apply full even coat liberally to timber. Allow approx 10 minutes to penetrate and "set". Wipe off excess with a soft lint free cloth, and finish wiping in direction of grain. For greater lustre apply a second coat of Danish Oil after allowing 8 hours drying. Sand very lightly between coats. Finish can be buffed using a pad or folded cloth. Alternatively, lightly sand while wet using 5/600 grit wet and dry paper, then buff.</p>

### Health And Safety

<b>MSDS Number</b>	14184501	<b>Using Safety Precautions</b>	For detailed information refer to the product label and the current Material Safety Data Sheet available through CABOT'S Sales and Customer Service Offices.
<b>MSDS Link</b>	<a href="http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014184501.pdf">http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014184501.pdf</a>		
<b>Health Effects</b>	Splashes to eyes will cause irritation. Prolonged contact with liquid is harmful and inhalation of vapour may produce respiratory irritation and headaches.	<b>Flammability</b>	This product is flammable.
<b>Protective Equipment</b>	Wear eye protection, protective clothing and gloves.	<b>Storage</b>	Store and use away from sources of heat and ignition.
<b>Disposal</b>	Do not contaminate stormwater with product or product washings. Do not pour product down the drain. Unwanted product should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collection. Empty containers should be left open in a well ventilated area to dry out. When dry, recycle the container via recycling programmes. Disposal of empty paint containers via recycling programmes may differ between local authorities. Check with your local council first.		
<b>In the case of emergency, please call 0800 734 607</b>			

### Precautions And Limitations

Do not apply product if temperature is below 10C or is likely to fall below 10C during the drying period.  
Moisture content of timber should be close to equilibrium moisture content, usually 10-15%, but not exceeding 15%, for satisfactory application.  
For interior use only.

### Transport And Storage

<b>Pack A</b>	871-82113	<b>Shipment Name</b>	PAINTS, flammable liquid, high flash point.
<b>Size</b>	4 Litre 1 Litre 500ml 250ml	<b>Weight</b>	3.8 Kg 1.0 Kg 500g 300g
<b>Flash Point</b>	43C	<b>UN Number</b>	1263
<b>Dangerous Goods Class</b>	3b	<b>Package Group</b>	III

#### Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "Orica" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118