

## Cabot's Exterior Varnish Stain Gloss

NZDW1588

<b>Part A</b>	525 LINE
---------------	----------

### Description

Cabot's Exterior Varnish Stain is a combined semi transparent stain and varnish that provides protection, colour and shine without hiding the grain. As it is water based, it is fast drying, so you can recoat after only 2 hours, and clean up is easy with water. Cabot's Exterior Varnish Stain is designed for use on exterior doors, windows, trim and outdoor furniture.

### Features

- Water based
- Semi-transparent
- Lightly pigmented
- Anti blocking properties
- UV Protection

### Benefits



- Fast dry, easy clean up and low odour
- Reveals grain and texture and counters the effects of the sun's rays.
- Stain and varnish in one application
- Prevents sticking on doors and frames
- Blocks out harmful UV rays preventing them from penetrating and damaging the surface while resisting colour fading

### Uses

Use CABOT'S Exterior Varnish Stain for exterior doors and timber trim.

### Performance Guide

<b>Weather</b>	Formulated for exterior use	<b>Salt</b>	Unaffected by splash and spillage
<b>Heat Resistance</b>	Softens at temperatures above 70C	<b>Water</b>	Excellent water resistance
<b>Solvent</b>	Sensitive to alcohol and hydrocarbon	<b>Abrasion</b>	Moderate resistance to abrasion
<b>Acid</b>	Suitable for splash (dilute only)	<b>Alkali</b>	suitable for splash (dilute only)

Typical Properties																											
<b>Gloss Level</b>	60% at 85 degrees	<b>Thinner</b>	Not required																								
<b>Colour</b>	Full range of timber colours	<b>Components</b>	1																								
<b>Number Of Coats</b>	3	<b>Toxicity</b>	Lead free. Dry film is non-toxic and conforms to AS1647, Part 3																								
<b>V.O.C. Level</b>	< 75g/L	<b>Sanding Properties</b>	Good																								
<b>Touch Dry</b>	30 Minutes																										
<b>Clean Up</b>	 Water																										
<b>Clean Up Description</b>	Thoroughly clean all equipment with clean water																										
<b>Application Method</b>	 Brush																										
<b>Application Conditions</b>	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;"><b>Solids By Volume</b></td> <td style="text-align: center;">38</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;"><b>Min</b></td> <td style="text-align: center;"><b>Max</b></td> <td style="text-align: center;"><b>Recommended</b></td> </tr> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align: center;">84</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td></td> <td></td> <td style="text-align: center;">32</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td style="text-align: center;">2 Hours</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td></td> <td></td> <td style="text-align: center;">12</td> </tr> </table>			<b>Solids By Volume</b>	38				<b>Min</b>	<b>Max</b>	<b>Recommended</b>	<b>Wet Film Per Coat (microns)</b>			84	<b>Dry Film Per Coat (microns)</b>			32	<b>Recoat Time (min)</b>	2 Hours	Indefinite		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>			12
<b>Solids By Volume</b>	38																										
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>																								
<b>Wet Film Per Coat (microns)</b>			84																								
<b>Dry Film Per Coat (microns)</b>			32																								
<b>Recoat Time (min)</b>	2 Hours	Indefinite																									
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>			12																								

Application Guide	
<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>▪ Note: Fill holes and imperfections with a suitable timber putty if required.</li> </ul> <p><b>BARE TIMBER</b> Allow timber to weather for 4-6 weeks. After this period, clean exterior surfaces with Cabot's Deck Clean following label instructions.</p> <p><b>PREVIOUSLY PAINTED OR VARNISHED TIMBER</b> Remove back to bare timber using a paint stripper, or sanding. For exterior surfaces, then clean with Cabot's Deck Clean following label instructions.</p> <p><b>PREVIOUSLY STAINED AND OILED TIMBER</b> For exterior surfaces, clean with Cabot's Deck Clean following label instructions. Test if the surface is ready for coating by sprinkling water on the timber. If the water beads on the surface, repeat the application of Cabot's Deck Clean. If water is absorbed into timber, it is ready for coating. For a more transparent look, sand timber back to bare before coating.</p> <p><b>WEATHERED AND GREY TIMBER</b> For best results, sand timber back to fresh substrate. Clean with Cabot's Deck Clean following label instructions.</p> <p><b>FIBRE CEMENT PRODUCTS SUCH AS HARDIEPLANK(TM)</b> For a timber effect on fibre cement products such as woodgrain HardiePlank(TM) , prepare fibre cement boards by cleaning, and then coating with Dulux Timbacryl or Dulux Weathershield X10 in a pastel shade.</p>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>▪ <b>APPLICATION</b> Stir thoroughly with a broad flat paddle before and during use. Apply liberally along the full length of the board including exposed edges and end grain by brush. The initial milky colour helps with even product application, drying to a semi-transparent finish. Apply three coats, allowing a minimum of 2 hours drying between coats. Leave doors and windows ajar while drying to avoid sticking. Avoid surface contact for several days to allow full curing.</li> </ul> <p><b>MAINTENANCE</b> Regular inspection of all coated surfaces is recommended. When recoating aged Exterior Varnish Stain, if in good condition, lightly sand and clean surfaces, then apply one or more additional coats. If the coating is in poor condition, thoroughly strip off the existing coating and prepare as for new bare timber.</p>

Health And Safety			
<b>MSDS Number</b>	14291001	<b>Using Safety Precautions</b>	Provide adequate ventilation. If using indoors keep windows and doors open during use and while drying.
<b>MSDS Link</b>	<a href="http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014545068.pdf">http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014545068.pdf</a>		
<b>Health Effects</b>	14545068 For advice contact a Doctor or Poisons Information Centre AUST 131 126, NZ 0800 764 766 SWALLOWED: Give plenty of water to drink. Seek medical advice. EYE: Rinse with plenty of running water. Seek medical help if irritation occurs. For further information or a copy of the Product Safety Data Sheet telephone Cabots Customer Service Department on AUST 1800 011 006, NZ 0800 222 687. For emergencies phone AUST 1800 033 111, NZ 0800 734 607	<b>Flammability</b>	This product is not flammable.
<b>Protective Equipment</b>	Wear eye protection, protective clothing and gloves.	<b>Storage</b>	Keep out of reach of children
<b>Disposal</b>	Do not contaminate stormwater with product or product washings. Do not pour product down the drain. Unwanted product should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collection. Empty containers should be left open in a well ventilated area to dry out. When dry, recycle the container via recycling programmes. Disposal of empty paint containers via recycling programmes may differ between local authorities. Check with your local council first.		
<b>In the case of emergency, please call 0800 734 607</b>			

Precautions And Limitations
<p>All drying times quoted at 25°C and 50% humidity. Cooler or more humid conditions may require longer. Do not apply this product in temperatures below 10°C or above 35°C. Do not apply when rain or heavy dew is expected during the drying period. In hot temperatures, do not apply in direct sunlight, cool the timber by lightly dampening with water and coat in the shade. Not suitable for use on walk-on areas</p>

Transport And Storage			
<b>Pack A</b>	525 LINE	<b>Shipment Name</b>	Not dangerous goods.No special transport requirements.
<b>Size</b>	1 Litre, 4 litre	<b>Weight</b>	1.2kg 4.8kg
<b>Flash Point</b>	NA	<b>UN Number</b>	NA
<b>Dangerous Goods Class</b>	NA	<b>Package Group</b>	NA

**Disclaimer**

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.  
DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "Orica" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118