

# I BUILT<sup>TM</sup> CORECLAD

## CORECLAD

January 2023


CoreClad textured, ACQ treated plywood cladding offers superior strength, durability and reliability. With sheets up to 3 metres long and no requirement to retreat cut ends, CoreClad is fast and easy to install.





### CoreClad Features:

- Individual veneer treatment before manufacture ensures treatment to the core.
- Cut edges do not need to be re-treated.
- Available in 2440mm, 2745mm and 3050mm long sheets.
- Band sawn face for a rough textured finish.
- Supplied Textured Grooved 150 and Textured.
- Manufactured from high strength plantation pine (F14).
- Manufactured to AS/NZS 2269: 2012. Third party Certified by the EWPA.
- Meets the Durability requirements of the NZBC for claddings.
- Install to E2/AS1 NZBC



Unpainted with Scarf Joint / Painted with Scarf Joint.

### Specification table

Edge profile	Shiplap
Surface finish	Band sawn, Band sawn grooved
Panel length (mm)	2440, 2745*, 3050* (* Scarf jointed)
Panel width/cover (mm)	1200 (Cover), 1220 (Sheet)
Panel thickness (mm)	12
Channel dimension (Grooved panel only)	9mm wide, 5mm deep, 150mm centres
Face/back grade	SD
Veneer species	Hoop Pine & Klinkii Pine
Weight	23kg (2440mm), 26kg (2745mm), 29kg (3050mm)
Treatment	H3.2 ACQ veneer treated (Alkaline Copper Quaternary)
Bond	Type A structural marine bond
Fixings and Flashings	Must be Stainless Steel. PVC flashings can be used.

For full product information



\*A scarf joint is used to manufacture 2745mm and 3050mm length sheets. Refer to the Design & Installation Guide for details.



149 Kerrs Rd, Wiri, Auckland

PO Box 76412, Manukau, Auckland 2241, New Zealand

Tech Info Line: 0800-022-352

Phone: +64-9-268 6540

sales@ibuilt.co.nz  
techinfo@ibuilt.co.nz

www.ibuilt.co.nz