

PGH™ Face Bricks

Refer to product table below for applicable product codes covered by this document

Issue **A - 9/2024**

Product Type & Application

PGH™ Face Bricks are kiln-fired bricks made predominantly from clay and shale fired at high temperatures, and are suitable for masonry veneer exterior cladding applications. Formerly known as Monier Bricks® through The Brickery®, PGH Bricks are now available in New Zealand through CSR® Building Products.

Compliance with the New Zealand Building Code

When correctly specified and installed, this product meets or contributes to compliance with the following performance requirements of the building code:

- **B1 Structure** B1.3.1, B1.3.2, B1.3.3(f, h, j) – PGH Face Bricks have been tested in accordance with AS/NZS 4455.1 to verify compliance with the minimum material quality standards as specified in B1/AS1.
- **B2 Durability** B2.3.1(a) – Bricks strength is demonstrated to meet the NZBC B2 – Durability requirements (NZS 4210 C2.1.4.5). Additionally, bricks have been tested in accordance to AS/NZS 4456.10 to determine exposure category and may be used depending on the exposure category requirement in Appendix 2.E of NZS 4210:2001.
- **C3 Fire affecting areas beyond fire source** C3.7(a) – Brick materials are deemed to be non-combustible as stated in the definition of terms in C/AS1.
- **C6 Structural stability** C6.1 – Brick materials are able to achieve an FRR of at least 30/30/30 as required by C/AS1 5.1.1.2. See Limitations of Use for more details.
- **E2 External Moisture** E2.3.2, E2.3.3, E2.3.5, E2.3.6, E2.3.7 – Face bricks meet the requirements of E2/AS2 9.2.2(1) when tested in accordance with AS/NZS 4456.8.
- **F2 Hazardous building materials** F2.3.1 – Bricks are not classified as hazardous according to criteria of WorkSafe New Zealand GHS 7. However, the fine dust in/on the supplied product may include respirable crystalline silica. Cutting, breaking, drilling, sawing, grinding, and finishing may generate hazardous dust. Refer to the product SDS at pghbricks.co.nz for more information.

Basis of Compliance

- Testing to AS/NZS 4455.1 and specific AS/NZS 4456 series standards across the following reports:
 - PGH NATA Lab Report No. 2024028 – Hartlands
 - PGH NATA Lab Report No. 2023035 – Gypsy Rose
 - PGH NATA Lab Report No. 2023078 – Crevole
 - PGH NATA Lab Report No. 2024014 – Alpine
 - PGH NATA Lab Report No. 2024013 – Devon
 - PGH NATA Lab Report No. 2024012 – Rockhampton
 - PGH NATA Lab Report No. 2024011 – Moon Dust
 - PGH NATA Lab Report No. 2023037 – Malt
 - PGH NATA Lab Report No. 2022062 – Dover
- Professional Assessment, AS1530.4 –
 - BRANZ Assessment FC11917-001, 20 October 2020.
- Acceptable Solutions and Verification Methods for New Zealand Building Code Clause B1 Structure Amendment 21, 2 November 2023.
- Acceptable Solutions and Verification Methods for New Zealand Building Code Clause B2 Durability Amendment 12, 5 November 2020.
- C1-C6 Protection from Fire Acceptable Solution C/AS1 Energy Efficiency, Acceptable Solution H1/AS1, Protection from fire for buildings with sleeping (residential) and outbuildings (risk group SH), Second edition, 2 November 2023.
- C/AS2 Acceptable Solution for Buildings other than Risk Group SH, For New Zealand Building Code Clauses C1-C6 Protection from Fire, Amendment 3, 2 November 2023.
- Verification Methods E2/VM1 and Acceptable Solutions E2/AS1, E2/AS2 and E2/AS3 For New Zealand Building Code Clause E2 External Moisture, Amendment 10, 5 November 2020.
- Acceptable Solutions and Verification Methods For New Zealand Building Code Clause F2 Hazardous Building Materials, Amendment 3, 1 January 2017.
- PGH Safety Data Sheet for PGH Clay Bricks and Pavers, 11 September 2024.

Specific Design or Installation Instructions

- PGH Face Bricks are suitable for masonry veneer exterior cladding applications. Other applications would require specific engineering design.
- Design and installation of masonry veneer exterior cladding shall be in accordance with Section 11 of NZS 3604:2011, NZS 4210:2001, and/or Verification Methods E2/VM1 and Acceptable Solutions E2/AS1, E2/AS2 and E2/AS3 For New Zealand Building Code Clause E2 External Moisture, Amendment 10, 5 November 2020.
- For general guidance on bricklaying refer to the Master Brick and Blocklayers® publication 'Brick Veneer Best Practice Guide' September 2023 Edition.

PGH™ Face Bricks

Limitations of Use

- **IMPORTANT:** Do Not Modify This Product: Compliance with the evidence of suitability data referenced in this document is only achieved by the product or configuration listed in this PTS.
- Design and installation of the wall system should be in accordance with the New Zealand Building Code.
- These products are only intended for masonry veneer exterior cladding applications.
- This product is not subject to any warning or ban declared by MBIE under section 26 of the Building Act 2004.
- AS 1530.4 Assessment for FRR is 60/60/60 for walls up to two storeys high. Weep holes must meet the requirements of a Type A area in C/AS2 5.4.

Conditions of Storage, Use & Maintenance

- Store in the original packaging in a cool, dry area, away from foodstuffs. Ensure packages are adequately labelled, and protected from physical damage.
- Bricks are not classified as hazardous according to criteria of WorkSafe New Zealand GHS 7. However, the fine dust in/on the supplied product may include respirable crystalline silica. Cutting, breaking, drilling, sawing, grinding, and finishing may generate hazardous dust. Refer to the product SDS at pghbricks.co.nz for more information.
- Brick cleaning after bricklaying is a specialist trade and should only be undertaken by a professional. The chemicals and high-water pressures used can easily damage the product, if not done correctly. Different brick textures and colours often have different cleaning considerations. Dry brushing bricks periodically when laying to remove residual mortar is an effective way to reduce the amount of effort required to clean bricks. Bricks should be cleaned within 2 to 14 days of laying.

Brick Cleaning Guides are available at Bricksnz.co.nz/manuals

Alternatively, please contact PGH on 0800 999 277.

Applicable Product Codes

COLOUR	BRICK WEIGHT [kg per m ²]	WORK SIZE (LxWxH) [mm]	DIMENSIONAL CATEGORY ¹	UNCONFINED COMPRESSIVE STRENGTH ² (f _{uc}) [MPa]	DURABILITY CLASS ³	PRODUCT CODE
Hartlands	<150	230 x 70 x 76	DW1	>45	Exposure Grade	137757
Gypsy Rose	<150	230 x 70 x 76	DW1	>35	Exposure Grade	141728
Crevole	<120	230 x 70 x 76	DW1	>15	General Purpose	464612
Alpine	<110	230 x 70 x 76	DW1	>15	Exposure Grade	468281
Devon	<110	230 x 70 x 76	DW1	>15	Exposure Grade	468282
Rockhampton	<120	230 x 70 x 76	DW1	>15	Exposure Grade	473763
Moon Dust	<110	230 x 70 x 76	DW1	>15	Exposure Grade	480538
#Dover	<140	230 x 70 x 76	DW1	>25	Exposure Grade	141722#
#Malt	<140	230 x 70 x 76	DW1	>30	Exposure Grade	141726#

¹ Tested in accordance with AS/NZS 4456 Method 3: Determining dimensions

² Tested in accordance with AS/NZS 4456 Method 4: Determining compressive strength of masonry units

³ Tested in accordance with AS/NZS 4456 Method 10: Determining resistance to salt attack

Product discontinued (October 2024).

PGH™ Face Bricks

Additional Product Data

COLOUR	Coefficient of Expansion ⁴ [mm/m/15 years]	Initial Rate of Absorption ⁵ (IRA) [kg/m ² min]	Cold Water Absorption ⁶ [%]	Luminous Reflectance Value ⁷ [%]	Solar Absorptance Value ⁷ [%]	Core Percentage ⁸ [%]
Hartlands	<1	<0.75	<10			≤30
Gypsy Rose	<1.4	<0.75	<10	20.3	64.6	≤30
Crevole	<1.6	0.5-1.5	<12	69.5	28.0	≤30
Alpine	<1	0.5-1.5	<10	61.0	34.5	≤30
Devon	<1	0.5-1.5	<10	48.8	41.1	≤30
Rockhampton	<1	0.5-1.5	<10	33.3	56.2	≤30
Moon Dust	<1	0.5-1.5	<10	40.8	50.0	≤30
#Dover	<2.4	0.5-1.5	<10			≤30
#Malt	<2	0.5-1.5	<10			≤30

⁴ Tested in accordance with AS/NZS 4456 Method 11: Determining coefficients of expansion

⁵ Tested in accordance with AS/NZS 4456 Method 17: Determining initial rate of absorption (suction)

⁶ Tested in accordance with AS/NZS 4456 Method 14: Determining water absorption properties

⁷ Tested in accordance with ASTM E903-20: Standard Test Method for Solar Absorptance, Reflectance, and Transmittance of Materials Using Integrating Spheres


⁸ Tested in accordance with AS/NZS 4456 Method 7: Determining core percentage and material thickness

Product discontinued (October 2024).

For all:

Potential for Lime Pitting	When assessed to AS/NZS 4456 Method 13	Nil to Slight
Potential for Efflorescence	When assessed to AS/NZS 4456 Method 6	Nil to Slight

Membership



CLAY BRICK & PAVER
MANUFACTURER'S ASSOCIATION

Clay Bricks and Pavers Manufacturer's Association New Zealand

PGH Bricks NZ, 14 The Furlong, Takapani, Auckland For further technical advice call 0800 806 313/ email orders@csr.co.nz

PGH Bricks NZ is a business division of CSR Building Products (NZ) Limited (NZBN 9429040750194)

CSR Building Products (NZ) Limited is a business division of CSR Building Products Limited (ABN 55 008 831 356)

The contents of this brochure are copyright protected and may not be reproduced in any form without prior written consent of CSR Building Products (NZ) Limited. Recommendations and advice regarding the use of the products described in this brochure are to be taken as a guide only, and are given without liability on the part of the company or its employees. We reserve the right to change product specifications without prior notification. Please refer to the PGH NZ website for the latest revision of this document. The purchaser should independently determine the suitability of the product for the intended use and application.

