

# VOC Emission Test Summary

Tuesday December 20<sup>th</sup>, 2011

Supplier: Regupol (Unit 2, 5 Cary Grove, Minto NSW 2566)

Date Tested: October 2007

Test Method: Carpet & Rug Institute Green Label test program incorporating  
ASTM D5116 "Standard Guide for Small-Scale Environmental Chamber  
Determinations of Organic Emissions from Indoor Material/Products".

Emission Data:

	Everroll	Everroll Granite
Total Volatile Organic Compound	2.3 mg/m <sup>2</sup> /hr	1.8 mg/m <sup>2</sup> /hr
Acetaldehyde	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Benzene	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Caprolactam	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
2-Ethylhexanoic Acid	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Formaldehyde	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
1-Methyl-2-Pyrrolidinone	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Naphthalene	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Nonanal	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Octanal	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
4-Phenylcyclohexene	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Styrene	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Toluene	0.10 mg/m <sup>2</sup> /hr	0.15 mg/m <sup>2</sup> /hr
Vinyl Acetate	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
2-Ethyl-1-Hexanol	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Hydrocarbons (C <sub>10</sub> – C <sub>14</sub> )	1.5 mg/m <sup>2</sup> /hr	1.0 mg/m <sup>2</sup> /hr
Vinyl Cyclohexene	<0.01 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Xylenes	0.1 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Methyl Isobutyl Ketone	0.5 mg/m <sup>2</sup> /hr	<0.01 mg/m <sup>2</sup> /hr
Trimethyl Benzenes	<0.01 mg/m <sup>2</sup> /hr	0.3 mg/m <sup>2</sup> /hr
Cumene	<0.01 mg/m <sup>2</sup> /hr	0.05 mg/m <sup>2</sup> /hr



Dr. Vyt Garnys  
PhD, BSc(Hons) AIMM, ARACI, ISIAQ  
ACA, AIRAH, FMA  
Managing Director and Principal Consultant

CV071002a